

# **MINERAL FIBRE Galvanised Lagging Mattress 4000GLM**

## **ADVANTAGES**

### **Durable - Safe - Cost effective**

- No organic binders – soft, flexible, vibration resistant and resilient even after heating
- Non combustible BS 476 part 4, ASTM C592-80, DIN 52275 part2
- Easy and safe to use. Non respirable. Non carcinogenic - European Carc. Cat. 0 (unclassified)

## **DESCRIPTION**

Lancaster Mineral Fibre Galvanised Lagging Mattress comprises unbonded mineral fibres securely stitched to galvanised hexagonal wire mesh to form a mattress with excellent thermal insulation properties, making this product ideal for external insulation lagging and cladding applications in construction projects. The unbonded nature of the product means that no charring or embrittlement occurs due to degradation of organic binder, making the mattress especially suitable for external insulating of hot industrial plant.



## **CHEMICAL COMPOSITION**

Lancaster Mineral Fibre Galvanised Lagging Mattress is manufactured from basaltic material, incorporating an addition of recycled fibres into the melt. An inherently low level of mineralogical calcite (CaCO<sub>3</sub>) is maintained, which gives the product very good resistance to attack by acidic residues. Oxide composition is given below:

Silicon oxide	SiO <sub>2</sub>	43-50%
Aluminium oxide	Al <sub>2</sub> O <sub>3</sub>	11-18%
Iron oxide	Fe <sub>2</sub> O <sub>3</sub>	10-15%
Calcium oxide	CaO	10-14%
Magnesium oxide	MgO	8-14%
Sodium oxide	Na <sub>2</sub> O	2-5%
Potassium oxide	K <sub>2</sub> O	0.5-3%
Titanium oxide	TiO <sub>2</sub>	2-4.5%
Residual mineralogy as CaCO <sub>3</sub>		0-0.05%

## **PHYSICAL CHARACTERISTICS**

Mean Filament Diameter (typical):	12um
Minimum Filament Diameter (as LWGM –2 standard errors):	>6um
Mean Filament Length:	80mm
Classification (EU Directive 97/69EC)	unclassified
Density:	100 kg/m <sup>3</sup> (6.25pcf)
Working temp at 80% Tmax:	600°C (1110°F)
Maximum working temperature:	750°C (1380°F)

## **THERMAL CONDUCTIVITY**

<b>Mean Temperature (°C)</b>	<b>10</b>	<b>50</b>	<b>100</b>	<b>150</b>	<b>200</b>	<b>250</b>	<b>300</b>	<b>350</b>	<b>400</b>
<b>Mean Temperature (°F)</b>	<b>50</b>	<b>132</b>	<b>212</b>	<b>300</b>	<b>390</b>	<b>480</b>	<b>570</b>	<b>660</b>	<b>750</b>
<b>'K' value (W/mk)</b>	<b>0.037</b>	<b>0.039</b>	<b>0.045</b>	<b>0.052</b>	<b>0.063</b>	<b>0.077</b>	<b>0.090</b>	<b>0.108</b>	<b>0.130</b>

## **AREAS OF APPLICATION**

Lancaster Mineral Fibre Galvanised Lagging Mattress is especially suitable for the external insulation of plant and equipment in the following industries:

- Power generation.
- Petroleum refining.
- Chemical processing.
- Paper making.

## **HEALTH AND SAFETY**

Lancaster Mineral Fibre Galvanised Lagging Mattress achieves the lowest possible risk rating under the EU categorisation of Man Made Vitreous Fibre (potential for carcinogenicity). Full MSDS data will be given on request.

## **OTHER MATERIALS**

For internal insulation applications in hot gas ducts, silencers and boilers, the Company manufactures GTB® thermal acoustic fibrous basalt materials, the international “benchmark” for gas turbine silencing.